



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Bronze Filled Polytetra Fluoroethylene

Suebel Code : BRT-40

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ASTM D 792, 23 °C	3.10-3.22	3.13	g/cm ³
Hardness ASTM D 2240, 23 °C	67-69	68	Shore D
Tensile strength ASTM D 1457, 23 °C	180-240	200	Kg/Cm ²
Elongation at break ASTM D 1457, 23 °C	240-320	280	%
Heat Distortion Temp at 0.5mpa	---	260	°C
Operating Temp Range	---	-270 to 260	°C
Filler Content	---	BRONZE-40 PTFE-60	% by Weight % by Weight

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB