



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Thermoplastic Polyurethane

Suebel Code : CPU

Revision date : 01/03/2009

Physical properties	Value	units
Density ISO 1183, 23 °C	1.13	g/cm ³
Hardness ISO 868, Shore A, 23 °C	93	Shore A
Hardness ISO 868, Shore D, 23 °C	42	Shore D
Tensile strength ISO 37	44.8	mpa
Elongation at break ISO 37, 23 °C	375	%
Abrasion ISO 37, 23 °C	18	%
Rebound resilience ISO 4662	40	%
Tear strength ISO 34B	140	K N/m
Compression set ISO 815, B, 22 °C, 70 h, 25 %	26	%
70 °C, 24 h, 25 %	35	%
Operating Temp	-35 to 110	°C

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB