



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Carboxylated Nitrile Butadiene Rubber

Suebel Code : NT 23B (X NBR)

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Hardness BS 903 A 26, 23 °C	70-75	72	Shore A
Tensile strength BS 903 A 2, 23 °C	> 142.8	165	Kg/Cm ²
Elongation at break BS 903 A 2, 23 °C	> 250	370	%
Compression set BS 903 A 6, 100 °C, 22 h, 25 %	< 25	21.2	%
Air Ageing BS 903 A 19, 100 °C, 70 h			
Hardness Change	<(±10)	+2	Points
Tensile Change	<(-20)	-15	%
Elongation Change	<(-30)	-13.5	%
Fluid Resistance, Liquid-B BS 903 A 16, 23 °C, 70 h			
Hardness Change	0 to -20	-4	Points
Tensile Change	<(-50)	-18	%
Elongation Change	<(-50)	-18.9	%
Volume Change	0 to +20	4.8	%
Fluid Resistance, ASTM Oil-3 BS 903 A 16, 100 °C, 70 h			
Hardness Change	-10 to +5	-3	Points
Tensile Change	<(-20)	-12.2	%
Elongation Change	<(-30)	-17.2	%
Volume Change	0 to +5	+3.8	%
Specific Gravity BS 903 A 1, 23 °C	---	1.22	Gm/cc
Ash Content 800°C, 2 Hrs	---	7.4	%

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB