



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Phenolic Resin Fabric

Suebel Code : PF-1(CPF)

Revision date : 01/03/2009

| Physical properties | nominal | actual | units |
|---|-----------|------------|-------------------|
| Density ISO-1183, 23 °C | 1.37-1.41 | 1.39 | g/cm ³ |
| Hardness ASTM D 785, 23 °C | M-89 | M-89 | Scale M |
| Tensile strength ISO 527 1, 23 °C | 49Min | 51 | mpa |
| Heat Distortion ISO 75 2,Temp at 0.5mpa | --- | 170 | °C |
| Operating Temp Range | --- | -20 to 120 | °C |

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB