



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Polyphenylene Sulfide with 40% Glass Filled

Suebel Code : PPS

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ASTM D 792, 23 °C	1.64-1.68	1.66	g/cm ³
Hardness ASTM D 785, 23 °C	M-100	M-100	Scale M
Tensile strength ASTM D 638, 23 °C	190Min	193	mpa
Elongation at break ASTM D 638, 23 °C	1.70Min	2.2	%
Heat Distortion ASTM D 648, Temp at 1.82mpa	---	270	°C
Operating Temp Range	---	270Max	°C

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB