



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Polytetra Fluoroethylene+10% EKONOL

Suebel Code : PTFE+10% EKONOL

Revision date : 01/03/2014

Physical properties	nominal	actual	units
Density ASTM D4745, 23 °C	2.10 ±0.02	2.11	g/cm ³
Hardness ASTM D 2240, 23 °C	53-59	57	Shore D
Tensile strength ASTM D4745,23 °C	> 25	27.5	mpa
Elongation at break ASTM D4745, 23 °C	> 300	340	%
Heat Distortion Temp at 0.5mpa	---	260	°C
Service Temp	---	-200 to 250	°C

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB