



Groot-Bijgaardenstraat 124  
B-1620 Drogenbos

## Material : Thermoplastic Polyurethane

Suebel Code : PU-5 (Food Grade)

Grade : PU for Food Contact Applications.

1) *Our Food Grade Compounds were successfully tested at IRMRA [ANABL (ISO-17025-2005) Accredited Laboratory] referring to US-FDA-177-2600.Clause(F).*

2) *All ingredients used in forming the compounds are from the reputed suppliers & food grade certified.*

Revision date : 01/03/2009

Physical properties	nominal	actual	units
<b>Density</b> ISO 1183, 23 °C	1.15 ±0.02	1.15	g/cm <sup>3</sup>
<b>Hardness</b> ISO 868, Shore A, 23 °C	88 - 92	90	Shore A
<b>Hardness</b> ISO 868, Shore D, 23 °C	38 - 42	40	Shore D
<b>Modulus</b> 300 %, ISO 37, 23 °C	---	11	mpa
<b>Tensile strength</b> ISO 37	> 45	48	mpa
<b>Elongation at break</b> ISO 37, 23 °C	> 610	650	%
<b>Rebound resilience</b> ISO 4662	---	40	%
<b>Tear strength</b> ISO 34B	---	65	%
<b>Compression set</b> ISO 815, B, 22 °C, 70 h, 25 % 70 °C, 24 h, 25 %	< 30 < 75	23 68	% %
<b>Heat Distortion</b> Temp at 0.5mpa	---	85	°C
<b>Operating Temp</b>	-30 to +100	---	°C

RC Bruxelles 543672  
TVA : BE 443 660 083  
Fortis Bank

Tel : 00 32 2 – 331 25 32  
Fax : 00 32 2 – 378 15 16  
IBAN : BB88 2100 9023 8041

Web : [www.suebel.be](http://www.suebel.be)  
Email : [sales@suebel.be](mailto:sales@suebel.be)  
Swift (BIC) : GEBABEBB