



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Fluorocarbon Viton Rubber

Suebel Code : VT 3B FG

Colour : Green.

Grade : Rubber for Food Contact Applications.

- 1) *Our Food Grade Compounds were successfully tested at IRMRA [A NABL(ISO-17025-2005) Accredited Laboratory] referring to US-FDA-177-2600.Clause(F).*
- 2) *All ingredients used in forming the compounds are from the reputed suppliers & food grade certified.*

Revision date : 01/04/2015

Physical properties	nominal	actual	units
As per BS 5176, Grade-1			
Hardness BS 903 A 26, 23 °C	80-85	82	Shore A
Tensile strength BS 903 A 2, 23 °C	> 102	135	Kg/Cm ²
Elongation at break BS 903 A 2, 23 °C	> 150	200	%
Compression set BS 903 A 6, 200 °C, 22 h, 25 %	< 50	32.8	%
Air Ageing BS 903 A 19, 250 °C, 70 h			
Hardness Change	<(±15)	+3	Points
Tensile Change	<(±30)	-14.8	%
Elongation Change	<(-50)	-20	%
Fluid Resistance, ASTM Oil No.3 BS 903 A 16, 150 °C, 70 h			
Volume Change	0 to +10	5.2	%
Specific Gravity BS 903 A 1, 23 °C	---	1.793	Gm/cc
Ash Content 800°C, 2 Hrs	---	7.65	%

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB